

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all previous versions, and listings, of claims in the Application.

Listing of Claims

Please amend the Claims as follows:

1. (Currently Amended) Process for assembly of aluminum alloy plates comprising fluxless brazing under controlled nitrogen and/or argon atmosphere at a temperature of between 580°C and 620°C, and rapid cooling, and in which at least one of the plates ~~includes~~ consists essentially of:

(a) a core alloy with composition (% by weight):

Si 0.3-1.0; Fe<1.0; Cu 0.3-1.0; Mn 0.3-2.0; Mg 0.3-3.0; Zn<6.0; Ti<0.1; Zr<0.3; Cr<0.3; Ni<2.0; Co<2.0; Bi<0.5; Y<0.5; other elements <0.05 each and ≤0.15 total, remainder aluminum, and

(b) ~~is an aluminum brazing alloy~~ coated on at least one face ~~of the core alloy, the with an~~ aluminum brazing alloy including ~~containing~~ 4% to 15% of silicon and 0.01% to 0.5% of at least one element selected from the group consisting of Ag, Be, Bi, Ce, La, Pb, Pd, Sb, Y or mischmetal.

2. (Original) Process according to claim 1, characterized in that the copper content of the core alloy is between 0.35% and 1%.

3. (Previously Presented) Process according to claim 1, characterized in that the manganese content of the core alloy is between 0.3% and 0.7%.

4. (Currently Amended) Process according to claim 1, characterized in that the manganese magnesium content of the core alloy is between 0.35% and 0.7%.

5. (Previously Presented) Process according to claim 1, characterized in that the zinc content of the core alloy is less than 0.2%.

6. (Previously Presented) Process according to claim 1, characterized in that the bismuth content of the core alloy is between 0.05% and 0.5%.

7. (Previously Presented) Process according to claim 1, characterized in that the yttrium content of the core alloy is between 0.01% and 0.5%.

8. (Currently Amended) Process according to claim 1, characterized in that composition of the core alloy is (% by weight):

Si 0.3-1.0; Fe<0.5; Cu 0.35-1.0; Mn 0.3-0.7; Mg 0.35-0.7; Zn<0.2; Ti<0.1; Zr<0.3; Cr<0.3; Ni<1.0; Co<1.0; Bi<0.5; Y<0.5; other elements <0.05 each and ≤ 0.15 total, remainder aluminum.

9. (Previously Presented) Process according to claim 1, characterized in that the brazing alloy is clad onto the core alloy by co-rolling.

10. (Previously Presented) Process according to claim 1, characterized in that the brazing alloy coating is composed of particles.

11. (Previously Presented) Process according to claim 1, characterized in that it is used for manufacturing of heat exchangers and that aging is conducted in hot parts during operation of exchangers.

12. (Previously Presented) Process according to claim 1, comprising aging at a temperature of between 80°C and 250°C after rapid cooling.

13. (Previously Presented) Process according to claim 10, wherein the particles are coated by a polymer resin.

14. (Previously Presented) A process for brazing aluminum alloy plates comprising:

(a) coating one or more plates with a cladding alloy comprising between 4% to 15% by weight silicon and 0.01% to 0.5% by weight of at least one element selected from the group consisting of Ag, Be, Bi, Ce, La, Pb, Pd, Sb, Y or mischmetal;

(b) subjecting the one or more plates to fluxless brazing under controlled nitrogen and/or argon atmosphere at a temperature of between 580°C and 620°C, and

(c) rapidly cooling the plates,

at least one of the plates including a core alloy comprising between 0.3% and 1.0% by weight silicon, between 0.3% and 3.0% by weight magnesium, between 0.3% and 2.0% by weight manganese, and between 0.3% and 1.0% by weight copper.

15. (Previously Presented) The process according to claim 14 also comprising aging at a temperature of between 80°C and 250°C after rapid cooling.

16. (Previously Presented) The process according to claim 14, wherein the core alloy also comprises between 0.05% and 0.5% by weight bismuth and/or 0.01% to 0.5% by weight yttrium.

17. (Previously Presented) The process according to claim 14, wherein the core alloy comprises between 0.35% and 0.7% by weight magnesium.

18. (Currently Amended) The process according to claim 14, wherein the core alloy comprises (% by weight):

Si 0.3-1.0; Fe<0.5; Cu 0.35-1.0; Mn 0.3-0.7; Mg 0.35-0.7; Zn<0.2; Ti<0.1; Zr<0.3; Cr<0.3; Ni<1.0; Co<1.0; Bi<0.5; Y<0.5; other elements <0.05 each and ≤0.15 total, remainder aluminum.

19. (New) A brazing sheet comprising:

a core alloy comprising (% by weight):

Si 0.3-1.0; Fe<0.5; Cu 0.35-1.0; Mn 0.3-0.7; Mg 0.35-0.7; Zn<0.2; Ti<0.1; Zr<0.3; Cr<0.3; Ni<1.0; Co<1.0; Bi<0.5; Y<0.5; other elements <0.05 each and <0.15 total, remainder aluminum; and

an aluminum brazing alloy coating at least one face of the core alloy, the brazing alloy comprising (% by weight):

4% to 15% of silicon and 0.01% to 0.5% of at least one element selected from the group consisting of Ag, Be, Bi, Ce, La, Pb, Pd, Sb, Y or mischmetal.

20. (New) A brazing sheet consisting essentially of:

a core alloy comprising (% by weight):

Si 0.3-1.0; Fe<1.0; Cu 0.3-1.0; Mn 0.3-2.0; Mg 0.3-3.0; Zn<6.0; Ti<0.1; Zr<0.3;
Cr<0.3; Ni<2.0; Co<2.0; Bi<0.5; Y<0.5; other elements <0.05 each and ≤ 0.15
total, remainder aluminum; and

an aluminum brazing alloy coating at least one face of the core alloy, the brazing alloy comprising (% by weight):

4% to 15% of silicon and 0.01% to 0.5% of at least one element selected from the group consisting of Ag, Be, Bi, Ce, La, Pb, Pd, Sb, Y or mischmetal.